

Patent
Attorney's Docket No. 000600-016

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Currently amended) A process for cleaning metals comprising the steps of
 - (a) contacting a metal with an aqueous solution comprising hydrogen peroxide, at least one mineral acid, and at least one compound selected from the group consisting of complexing agents based on phosphonic acids, salts and degradation products thereof in an amount from about 10 to about 60 wt% based on the amount of hydrogen peroxide, said solution having a pH of below 7; and
 - (b) cleaning said metal via said contacting step.

2. (Original) A process as claimed in claim 1, wherein the aqueous solution comprises at least one compound selected from the group consisting of complexing agents based on phosphonic acids, salts and degradation products thereof in an amount from about 20 to about 50 wt% based on the amount of hydrogen peroxide.

3. (Original) A process as claimed in claim 2, wherein the aqueous solution comprises at least one compound selected from the group consisting of complexing agents based on phosphonic acids, salts and degradation products thereof in an amount from about 35 to about 45 wt% based on the amount of hydrogen peroxide.

Patent
Attorney's Docket No. 000600-016

4. (Original) A process as claimed in claim 1, wherein the complexing agent is based on at least one compound selected from the group consisting of 1-hydroxyethylidene-1, 1-diphosphonic acid, 1-aminoethane-1, 1-diphosphonic acid, aminotri (methylenephosphonic acid), ethylene diamine tetra (methylenephosphonic acid), hexamethylene diamine tetra (methylenephosphonic acid), diethylenetriamine penta (methylenephosphonic acid), diethylenetriamine hexa (methylenephosphonic acid), salts and degradation products thereof.

5. (Currently amended) A process as claimed in claim 4, wherein the complexing agent is based on at least one compound selected from the group consisting of 1-hydroxyethylidene-1, 1-diphosphonic acid, salt and degradation products thereof.

6. (Original) A process as claimed in claim 1, wherein the solution comprises hydrogen peroxide in an amount from about 0.5 to about 20 wt%.

7. (Cancelled)

8. (Currently amended) A process as claimed in claim 7 1, wherein the ~~solution~~ mineral acid comprises sulfuric acid.

9. (Currently amended) A process as claimed in claim 8, wherein the ~~solution comprises~~ sulfuric acid is present in an amount from about 0.5 to about 20 wt%.

Patent
Attorney's Docket No. 000600-016

10. (Original) A process as claimed in claim 1, wherein the solution comprises at least one surfactant.

11. (Original) A process as claimed in claim 10, wherein the solution comprises at least one non-ionic surfactant.

12. (Original) A process as claimed in claim 1, wherein the metal is selected from the group consisting of aluminium, copper and steel.

13. (Currently amended) A process for cleaning metals comprising the steps of

(a) contacting a metal with an aqueous solution comprising sulfuric acid in an amount from about 0.5 to about 20 wt%, hydrogen peroxide and at least one compound selected from the group consisting of complexing agents based on phosphonic acids, salts and degradation products thereof in an amount from about 35 to about 50 wt% based on the amount of hydrogen peroxide, said solution having a pH of below 7; and

(b) cleaning said metal via said contacting step.

14. (Currently amended) A process as claimed in claim 13, wherein the complexing agent is based on at least one compound selected from the group consisting of 1-hydroxyethylidene-1, 1-diphosphonic acid, salts and degradation products thereof.

15. (Currently amended) A process for cleaning metals comprising the steps of

Patent
Attorney's Docket No. 000600-016

(a) contacting a metal with an aqueous solution comprising at least one mineral acid, at least one non-ionic surfactant ~~surfactant~~, hydrogen peroxide and at least one compound selected from the group consisting of complexing agents based on phosphonic acids, salts and degradation products thereof in an amount from about 10 to about 60 wt% based on the amount of hydrogen peroxide, said solution having a pH of below 7; and

(b) cleaning said metal via said contacting step.

16. (Currently amended) A process as claimed in claim 15, wherein the complexing agent is based on at least one compound selected from the group consisting of 1-hydroxyethylidene-1, 1-diphosphonic acid, salts and degradation products thereof.

17. (New) A process as claimed in claim 1, wherein said aqueous solution has a pH of from about 0 to about 6.

18. (New) A process as claimed in claim 1, wherein said aqueous solution has a pH of from about 0.5 to about 5.

19. (New) A process as claimed in claim 13, wherein said aqueous solution has a pH of from about 0 to about 6.

20. (New) A process as claimed in claim 13, wherein said aqueous solution has a pH of from about 0.5 to about 5.

Patent
Attorney's Docket No. 000600-016

21. (New) A process as claimed in claim 15, wherein said aqueous solution has a pH of
from about 0 to about 6.

22. (New) A process as claimed in claim 15, wherein said aqueous solution has a pH of
from about 0.5 to about 5.